



Technical specifications

PURE 540 Plain Merino wool

Art. N° 16

Composition	DIN 60001	100% Pure new wool (WV), Merino extra fine
Usable width	DIN EN 1773	Min. 150 cm
Mass per unit area	DIN EN 12127	360 g/m ² (540 g/lm)
Pilling resistance (Martindale)	DIN EN ISO 12945-2	3-4 at 7.000 rubs
Abrasion resistance (Martindale)	DIN EN ISO 12947-2	40.000 abrasion cycles
Colour fastness to rubbing, dry	DIN EN ISO 105-X12	4-5
Colour fastness to rubbing, wet	DIN EN ISO 105-X12	4-5
Colour fastness to light	DIN EN ISO 105-B02	4-6 (depending on colour)
Colour fastness to water	DIN EN ISO 105-E01	4
Colour fastness to perspiration	DIN EN ISO 105-E04	4
Oil repellence	AATCC 118	6
Piece length	Ca. 50 meters	
Recommended use	Jackets, Overcoats, Uniforms	
Care instructions		

 Note: Subject to change depending on technical upgrades. Values indicated without their specific tolerance levels are nominal values with a tolerance of $\pm 5\%$. All data presented is given to the best of our current knowledge for guidance purposes and is not legally binding. The technical data in the material data sheet is based on experience from current productions and does not constitute any quality agreement. This data refers to goods in ex-works condition without any processing or handling by the customer. The given data is informative only and merely serves as a guide. It will in no way release the customer from checking the suitability of the intended use, before processing and/or treatment.

Leichtfried

EST. 1884